

**EME-G700LA Type L-A**

## TYPICAL PROPERTIES:

<u>ITEM</u>	<u>TEST METHOD</u>	<u>UNIT</u>	<u>VALUES</u>
SPIRAL FLOW	SB-U-03-003	cm	145
GEL TIME (at 175°C)	SB-U-03-005	sec	45
THERMAL EXPANSION $\alpha_1$	SB-U-02-002	X 10 <sup>-5</sup> 1/°C	1.0
THERMAL EXPANSION $\alpha_2$	SB-U-02-002	X 10 <sup>-5</sup> 1/°C	3.9
T <sub>g</sub>	SB-U-02-002	°C	125
THERMAL CONDUCTIVITY	SB-U-02-004	W/m •°C	96x 10 <sup>-2</sup>
FLEXURAL STRENGTH	SB-U-01-001	N/ mm <sup>2</sup>	
(at 25°C)			165
(at 260°C)			16
FLEXURAL MODULUS	SB-U-01-002	X 10 <sup>2</sup> N/mm <sup>2</sup>	
(at 25°C)			21500
(at 260°C)			6.5
SPECIFIC GRAVITY	SB-U-03-018	-----	1.99
VOLUME RESISTIVITY	SB-U-00-004	$\Omega$ - cm	1 x 10 <sup>12</sup>
(at 150°C)			
UL FLAME CLASS	SB-U-03-003	UL-94	V-0
WATER ABSORPTION	SB-U-03-002	% weight gain	0.14
(boiling, 24 h)			
EXTRACTED Na <sup>+</sup>	SB-U-04-043	ppm	1
EXTRACTED Cl <sup>-</sup>	SB-U-04-043	Ppm	5

TYPICAL, NOT GUARANTEED PROPERTIES

## MOLDING AND POST MOLD CURE CONDITIONS:

	<u>STANDARD</u>	<u>RANGE</u>
TRANSFER PRESSURE	100 x 10 <sup>5</sup> Pa	70-120 x 10 <sup>5</sup> Pa
MOLD TEMPERATURE	180°C	165-185°C
CURE TIME (C or A)#	A/90 sec	60-120 sec
POST-MOLD CURE TEMP	175°C	170-180°C
POST-MOLD CURE TIME	6 h	4-8 h

#Conventional or Auto

rev. Feb. '12

The information contained herein is true and accurate to our best knowledge. Sumitomo Bakelite Co., Ltd. , makes no warranty or guarantee of results and assumes no obligation or liabilities from the use of any products mentioned herein. This publication is not to be taken as license to operate under or recommendations to infringe upon any patents.

