




### TOP VIEW





SECTION A-A

### SIDE VIEW



### BOTTOM VIEW



MODEL

NOTES: (Unless Otherwise Specified).

1) MATERIAL:

A) LID:  $Al_2O_3$  BLACK CERAMIC. ALUMINA 91%

B) PREFORM: B-STAGE THERMOSET EPOXY LCA1000X.

2) RECOMENDED CURE: WITH CLAMP PRESSURE 0.035KG/CM SQ.

STEP 1 - PREHEAT PACKAGE @ 75 °C

STEP 2 - CURE AT 125°C FOR 30 MINUTES.

STEP 3 - CURE AT 150°C FOR 60 MINUTES.

3) STORAGE LIFE: 6 MONTHS @ 25°C. 12 MONTHS @ 0°C.

4) DIMENSIONS IN MM.

APPROVALS	DATE	<b>TopLine®</b>			
DRAWN T. Au	4/29/2021				
ENG M. Hart	4/29/2021	TITLE CERAMIC LID FOR SOL24 WITH B-STAGE EPOXY			
MFG		SCALE 16:1	SIZE A	DRAWING NO. 228073	REV C
QA		DO NOT SCALE DRAWING		SHEET 1 OF 1	
CUST					
REVISED					